

OPTAPIX KG 6

Binder for glazes and engobes



Chemical basis:

Highly purified sodium carboxymethylcellulose (CMC)

Characteristics:

Appearance:	white powder
Moisture content:	8 % maximum
Solubility:	water-soluble
Bulk density:	approx. 700 g/l
pH (1 %):	approx. 7
CMC content dry:	approx. 99 %
Viscosity (4 %, 25 �C):	approx. 35 mPas

Shelf-life / Packaging:

12 months when stored under proper and dry conditions
bags of 20 kg

Application:

OPTAPIX KG types differ by their degrees of polymerisation and hence the viscosities of their aqueous solutions.

These additives are used in glazes and engobes as viscosity adjusting, non-foaming binding agents. They improve the abrasion resistance, give glazes or engobes a good fit and prevent running.

Sodium CMC being a polyelectrolyte, the low viscosity, i.e. short-chain types like OPTAPIX KG 6 have a deflocculating effect besides their binding property.

As far as the sodium CMC types with a medium degree of polymerisation such as OPTAPIX KG 50 are concerned, their electrolytic effect is to a large extent compensated by their increased intrinsic viscosity; they, therefore, have a rather neutral effect on the viscosity of the glaze slip, at the usual addition quantities.

High polymer types such as OPTAPIX KG 1000 have a thickening effect on the glaze slip. In general, an increasing degree of polymerization will lead to better binding properties and to an improved dehydration, this means the drying time increases.

Further advantages of OPTAPIX KG types are their plasticizing effect on ceramic bodies and an improved dry breaking strength.

The above results have been obtained from trials in our laboratory and plant. In the light of changing conditions they can serve only as a guide and are therefore offered without obligation. We ask you to observe the possible rights of third parties.

Issued: 10. October 2013

Page: 1 / 2



OPTAPIX KG 6

The addition quantity giving optimum results is between 0.05 and 1.0 %, the correct amount depending on the individual working conditions. They are milled with the glaze constituents or added as aqueous stock solution.

Note:

Solutions of OPTAPIX KG 6 are relatively resistant to decomposition. However, if they are to be stored over longer periods, they should be preserved with one of our NOVAL types.

The above results have been obtained from trials in our laboratory and plant. In the light of changing conditions they can serve only as a guide and are therefore offered without obligation. We ask you to observe the possible rights of third parties.

Issued: 10. October 2013

Page: 2 / 2

